



Silica sand

Plant: HAIDA

Silica sand

kiln-dried

Grain size in mm

HQs 0.1 – 0.4

HQs 0.2 – 0.6

HQs 0.2 – 0.7

HQs 0.3 – 0.8

HQs 0.4 – 0.8

HQs 0.5 – 0.8

HQs 0.5 – 1

HQs 0.7 – 1.2

HQs 1.0 – 1.6

HQs 1 – 2

HQs 0 – 2

Joint sand

Physical parameters

Density	2.65 Mg/m ³
Bulk density	~ 1.50 Mg/m ³
Shape	edge rounded
Sintering point	> 1450 °C
pH-value VDG-Specification P 26	~ 7
Residual moisture	≤ 0.1 %
Clay content / porportion of fines	< 0.3 %
Hardness (Mohs)	~ 7

Chemical parameters

SiO₂ ~ 97,20 %

Fe₂O₃ ~ 0,10 %

Al₂O₃ ~ 1,73 %

Our products can be offered on costumer's demands and for all customer-specific requirements.

Technical data sheets upon request.

Packaging services:

Different package sizes (big bags, plastic sack (25kg, 5kg) or paper valve sack (25kg))

Supply of filtersand and -gravel in bulk form (silo trucks)

Transport security:

Europallets, IPPC-pallets, shrink-wrapped, big bag

Prices:

Upon request

Surcharge for small quantities:

When delivering quantities less than 1 t a quantity surcharge of 100% will be added to the material price.

Energy surcharge:

The determination of the energy surcharge for the current month are accounted by the purchase price of heating oil in the first week of the month.

The deliveries, performance and offers of our company shall be based exclusively on our Terms and Conditions. These you can view or download at www.wm-quarzwerke.com.

Screening is performed by vibrationmaschine AS200 Control of Retsch (sample weight 200g sand / 500g gravel, screening time 5 min, amplitude 1.5 plant Haida).

Certification:

DIN EN ISO 9001:2015

DIN ISO 50001:2011

Sieve set DIN ISO 3310 part 1

